

Customer INFORMATION



BIODUR®
Products GmbH

06/2016

Modified composition of BIODUR® E 12 and other products.

Dear BIODUR® customers,

Due to European legislation several substances of very high concern (SVHC) are no longer available on the free market.

Affected by this development are raw materials for the products **BIODUR® E 12, BIODUR® E 13** and **BIODUR® AE 10**.

In response to this new situation **BIODUR® Products** has carried out tests in the recent months with the aim to provide our customers with reliable epoxy resin systems for sheet plastination and histological applications.

This letter is to inform you about the results and changes in our product range.

BIODUR® E 12

BIODUR® E 12 remains as a sales product. Its physical and chemical properties are widely equal those of the known E 12 which have been proven for decades. The mixing ratios for each of the application relevant hardeners (**BIODUR® E 1, BIODUR® E 6** and **BIODUR® E 7**) remain unchanged. The newly developed **E 12** shows no cmr* health hazards. All of the above also apply to the special resin **BIODUR® E 13**.

BIODUR® AE 10

BIODUR® AE 10 will no longer be available. Instead, we are introducing our new product, **BIODUR® AE 20**, which will be added to **E 12** as plasticiser, depending on the application. Besides the reduced health hazard characteristics, the added benefit is that **AE 20** is not classified as a dangerous good, according to the current regulations for road, sea and air transportation.

*carcinogenic, mutagenic, toxic to reproduction

BIODUR® Products remains committed to offer you the best possible solutions. Therefore, we continue developing alternative plasticisers, which are increasingly better suited for specific applications. We will continue to inform you with results as we complete testing and add new products.



RECOMMENDED MIXING RATIOS*

Sheet plastination (sandwich/drain method)	BIODUR® E 12	100
	BIODUR® AE 20	20
	BIODUR® E 1	28
Sheet plastination (flat chamber method), cast and impregnation resin	BIODUR® E 12	95
	BIODUR® AE 20	20
	BIODUR® AE 30	5
	BIODUR® E 1	26
Histological applications	BIODUR® E 12	100
	BIODUR® E 1	28
Transparent slices for histological purposes	BIODUR® E 12	100
	BIODUR® E 6	50
	BIODUR® E 600	0,5 ml
Ground sections	BIODUR® E 12	100
	BIODUR® AE 20	0-10
	BIODUR® E 7	70
	BIODUR® E 700	0,2 vol-%
Transparent body slices (formulation with long processing time)	BIODUR® E 13	100
	BIODUR® E 8	58

* All amounts in parts by weight, unless otherwise indicated.